Hardness conversion of thin Hardox® wear sheet

General Product Description

Thin Hardox® wear sheet offers an effective wear solution even below 2.5 mm thickness.

Hardox® wear sheet is an abrasion-resistant steel with a nominal hardness range between 400 - 500 HBW. This document serves as a formal supplement to existing datasheets, it is recommended to review this document alongside the original product datasheet.

Brinell hardness testing is less suitable for very thin gauges. Hence, the tensile strength is measured and guaranteed. The corresponding hardness is calculated by material specific conversion based on a thickness range where both Brinell Hardness and tensile strength are consistent measurement methods.

Mechanical Properties

Product	Thickness (mm)	Typical hardness (HBW), not guaranteed	Tensile strength R_m (MPa)	Typical yield strength (MPa), not guaranteed
Hardox® 400 sheet	2.0 - 2.49	370 - 430	1190 - 1390	1100
Hardox® 450 CR sheet	0.8 - 2.10	425 - 475	1390 - 1560	1250
Hardox® 450 sheet	2.0 - 2.49	425 - 475	1390 - 1560	1250
Hardox® HiAce sheet	2.0 - 2.49	425 - 475	1390 - 1570	1250
Hardox® 500 sheet	2.0 - 2.49	470 - 530	1560 - 1740	1400
Hardox® 500 Tuf sheet	2.0 - 2.49	475 - 505	1540 - 1650	1370

Contact Information

www.ssab.com/contact

SSAB, Strenx, Hardox, Docol, GreenCoat, Toolox, Armox, Ramor, SSAB Domex, SSAB Laser, Raex, Duroxite are trademarks owned by the SSAB group of companies.